

SYRANOL GOLD

SAE Grade	10 W	30	40
Specific Gravity @ 15c	0.881	0.894	0.898
Viscosity @ 40c	36.0	92	145
Viscosity @ 100c	6.1	11.1	15.9
Viscosity index	112	105	120
Base Number	6.2	6.2	7.7
Sulphated Ash	0.8	0.8	0.8
Open cup flash point .C	218	240	259
Pour point .C	-27	-21	-16