

SYRANOL Metal Working Fluid

ISO Grade	SYRANOL Metal Working Fluid	TEST METHOD
Speci_cGravity @ 15 °C	0.895	D-4052
Color	L 5.0	D-1500
Viscosity @ 40°C	37.0	D 445
@ 100°C	5.85	D 445
Refractomer Factor	1.0	
pH of 5% emulsion	9.5	
Corrosion test (20:1)	Pass	IP 287
Temperature, °C		
· Flash point, PMCC, °C	196	D-93
· Pour Point, °C	-9	D 97