

## SYRANOL industrial gear oils

ISO Grade	ISO 150	ISO 220	ISO 320	ISO 460	TEST METHOD
Specific Gravity @ 15 °C	0.888	0.892	0.901	0.904	D-4052
Color	2.5	L 3.0	L 3.5	L 3.5	D-1500
Viscosity @ 40°C	141.7	219.8	315.0	475.8	D 445
@100°C	14.26	26.04	26.04	31.0	D 445
Viscosity Index	98	100	100	96	D-2270
Copper Strip Corrosion 3 hrs @ 100 °C	1A	1A	1A	1A	D-130
FZG Scoring, Stage Passed	+12	+12	+12	+12	DIN 51544
Timken OK Load, lb	60	60	70	70	D-943
Temperature, °C					
· Flash Point, COC, °C	254	264	278	288	D-92
· Pour Point, °C	-15	-12	-9	-9	D 97